

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau




(43) International Publication Date
4 March 2004 (04.03.2004)

PCT

(10) International Publication Number
WO 2004/018590 A1

- (51) International Patent Classification⁷: C09K 11/78, 11/67, 11/68, 11/69, 11/82
- (74) Agents: ELLIS-JONES, Patrick, George, Armine et al.; J.A. Kemp & Co., 14 South Square, Gray's Inn, London WC1R 5JJ (GB).
- (21) International Application Number: PCT/GB2003/003649
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (22) International Filing Date: 20 August 2003 (20.08.2003)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data: 0219409.0 20 August 2002 (20.08.2002) GB
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- (71) Applicant (*for all designated States except US*): OXONICA LIMITED [GB/GB]; Unit 7, Begbroke Science & Business Park, Sandy Lane, Yarnton, Kidlington, Oxfordshire OX5 1PF (GB).
- (72) Inventors; and
- (75) Inventors/Applicants (*for US only*): GREEN, Mark [GB/GB]; c/o Oxonica Limited, Unit 7, Begbroke Science & Business Park, Sandy Lane, Yarnton, Kidlington, Oxford OX5 1PF (GB). WAKEFIELD, Gareth [GB/GB]; c/o Oxonica Limited, Unit 7, Begbroke Science & Business Park, Sandy Lane, Yarnton, Kidlington, Oxford OX5 1PF (GB).
- Published:
- with international search report
 - before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



WO 2004/018590 A1

(54) Title: LUMINESCENT COMPOUNDS

(57) Abstract: A luminescent particle is described having the formula: $M^2[M^1(POM)]$ wherein: M^2 is a cation, M^1 is an ion of a metal capable of providing a luminescent centre or a mixture of two or more thereof, and POM is a polyoxometallate, polythiometallate or polyoxothiometallate of at least one metal of group VA or VIA of the Periodic Table and, optionally, a hetero atom, X, the amounts of X, M^1 , M^2 and POM being such as to provide overall neutrality.


LUMINESCENT COMPOUNDS

5 This invention relates to luminescent compounds that will absorb in the near UV (defined at least 300nm) and emit in the visible. Such compounds are of potential use as luminescent tags in a biological diagnostic system or in luminescent security tags.

10 Most conventional phosphor materials are excited by 200-300nm UV. This makes such materials of little use for biotagging purposes because these wavelengths are strongly absorbed by biological molecules such as DNA. Accordingly, there is a real need for luminescent centres that excite in the near UV and/or short wavelength blue and which can, nevertheless, be used in biotagging purposes. Excitations from greater than 300 to 400 nm are therefore preferred. In addition, materials which have the potential of being used as a biotag must fully disperse in water and be capable of
15 being incorporated in, typically, silica spheres or other surface coatings which enable them to be attached to the biological molecule. Unfortunately, known materials of rare earth elements such as europium, while absorbing in the near UV and emitting in the visible, are quenched in water via a de-excitation state via a hydroxyl ion. This is
20 a non-radiative effect with the result that the known materials cannot be used for this purpose.

According to the present invention it has surprisingly been found that it is possible to produce luminescent material derived from polyoxo/thiometallates which can coordinate with luminescent centres such as lanthanides such that efficient
25 luminescence can be pumped from the near UV.

According to the present invention there is provided a luminescent particle comprising one or more compounds of the formula:



30 wherein:

-2-

M^2 is a cation, generally an ion of hydrogen or a metal of group 1A or 2A of the Periodic Table or an optionally substituted ammonium ion, or a mixture of two or more said ions,

M^1 is an ion of a metal capable of providing a luminescent centre or a mixture of two or more thereof, and

POM is a polyoxometallate, a polythiometallate or a polyoxythiometallate (optionally having a hetero atom X as explained below) of at least one metal of group VA or VIA of the Periodic Table, the amounts of X, M^1 , M^2 and POM being such as to provide overall neutrality.

Where a particle contains more than one such compound, then the different compounds thereof may differ in any one or more of the M^2 , M^1 , POM or X that they contain. The particles may consist primarily of (i.e. at least 50% by weight of), and preferably consist substantially entirely of (say at least 95% by weight of), the compounds defined above. However, where other materials are present, those other materials may comprises one or more other phosphors. Also, the present particles may be mixed with or otherwise used in conjunction with particles of other phosphors. This can result in a combination of, say, green and red emissions.

Metals of group V and VI of the Periodic Table, (see Chemistry of the Elements, Greenwood & Earnshaw, Pergamon, 1984), notably vanadium, niobium, tantalum, molybdenum and tungsten, are able to form, in their highest oxidation state, metal oxygen/sulphur cluster ions known as polyoxo/thiometallates, and are collectively referred to herein for convenience as "POM". The invention will be discussed principally in terms of oxo embodiments but it is to be understood that the comments made apply also to the thio and mixed embodiments. The majority of structures are constructed from these transition metals as polyhedrons and may be viewed as arrangements of edge and vertex sharing MO_6 octahedra and have one or two terminal oxygen ions although other polyhedral structures can be formed. At present we prefer POM structures that are symmetrical. It is believed that these POM have a crystal structure which excludes water ions from the inner coordination shell of the emitting ion and which effectively protects europium or other lanthanides from

water such that the compounds are not quenched by water.

M^2 can generally be any cation which does not interfere with the luminescence of the particle. Therefore it should not be an M^1 metal and generally not a transition metal. It is typically an ion of hydrogen or group IA or IIA of the Periodic Table or an optionally substituted ammonium ion. Typically, M^2 is potassium or sodium or NH_4 . However, the ammonium ion may be substituted by, for example, aliphatic or aromatic groups, typically alkyl groups of 1 to 6 carbon atoms such as methyl, ethyl, propyl or butyl and phenyl. All four hydrogen atoms can be replaced by substituents or 1, 2 or 3 hydrogen atoms can remain. A typical organic counterion is tetrabutyl ammonium. M^2 does not play an active role in the luminescence and acts as a counterion for the remainder of the molecule.

As indicated, M^1 is a metal capable of providing a luminescent centre and is typically a lanthanide although other metals including transition metals such as chromium, titanium and manganese can also be used. Typical ions include Eu^{3+} , Tb^{3+} , Dy^{3+} , Tm^{3+} , Er^{3+} , Cr^{3+} , Ce^{3+} , Pr^{3+} , Sm^{3+} , Nd^{3+} , Ho^{3+} , Yb^{3+} , Ti^{4+} , Mn^{2+} and Mn^{4+} . Preferred ions include Eu^{3+} , Tb^{3+} and Dy^{3+} . In this connection it should be pointed out that, europium, in particular, has in the past been incorporated in POMs but this has been for the purpose of examining crystal structure. In other words there has been no suggestion that the compounds could be used in biotagging or other such applications.

POM is a polyoxo/thiometallate of a group V or group VI metal, in particular vanadium, niobium, tantalum, molybdenum and tungsten, the last two being particularly preferred.

As indicated above, the crystal structure of the POM is particularly important in providing a "shield" for the luminescent centre which is incorporated in it. In addition, in order to maintain a high quantum efficiency, energy transfer from charge transfer state to the optically active centre must be efficient. This is believed to be governed by the de-localisation of the electron wave function over the POM structure and this is in turn governed by the M-O-M or M-S-M bond angles. It has been found that this structure can be modified by incorporation of a "heteroelement" X in the

POM, where X is for example a transition metal or an element such as B, Al, Si, P, S, Ga, Ge, As, Se, In, Sb, Te, I, Pb or Bi. The use of Si or Al is particularly preferred. The precise nature of the heteroelement is generally unimportant provided that it will form O-M-O-X- linkages.

5 It is believed that the nature of M governs the absorption wavelength of the light while, of course, M^I governs the emission. As previously indicated, the heteroelement X can have an effect on the bond angles i.e. the structure which is important for the delocalisation of an electron. It is believed that X does not in itself govern either luminescence or emission.

10 It is a particular feature of polyoxo/thiometallates that they are frequently formed from more than one metal. Typically M is a mixture, for example of molybdenum and tungsten. Also the number of oxygen atoms which are included in the structure frequently exceeds 10 and is typically 15 to 50. Examples include $M_{10}O_{36}$, M_6O_{18} and $M_{11}O_{39}$; of course the number of oxygen atoms is affected by M^I and X.

15 It is a further surprising feature of the present invention that the resulting particles possess a high quantum efficiency which is maintained in aqueous solution as well as in the dry state. In general, the particles will possess a quantum efficiency of at least 1%, preferably at least 5%, more preferably at least 20% and especially at least 35%.

20 The particles of the present invention can generally readily be made by a self-assembly procedure in an acidified medium. They can generally be prepared by mixing a water soluble source of M^2 with a water soluble salt of oxo/thiometallate in water or an aqueous solution. Acid, such as hydrochloric or acetic acid, is then added and then generally heated, typically to a temperature of 80° to 90°C. Generally the
25 pH of the solution will be 8 to 9 and this is reduced to, say, 6.5 to 7.5 by the acid. In general, the degree of acidification affects the final structure of the compounds. If a strong acid is added too quickly to produce a pH of less than 3 locally, then this generates product that is non-luminescent. Finally, a water soluble salt of the metal
30 capable of providing the luminescent centre is added, typically as a halide, for

-5-

example chloride, which is preferred, or nitrate. This generally results in a precipitate enabling the particles to be recovered. Sometimes the precipitate dissolves on stirring. The resulting solution, optionally filtered, can then be cooled to cause the desired product to crystallise.

5 It has been found that it is generally better to use the same cation for the ingredients as that of the desired M^2 .

It is also possible to form oxo/thiometallate by a solid state reaction, for example by high temperature firing, and to form the final lanthanide-activated compound by reaction with the complex lanthanide at neutral or basic pH.

10 Monomeric oxometallates such as WO_4^{2-} , and MoO_4^{2-} condense in an aqueous acidic media. As there are no electrons available from metallic bonding (due to the maximum valency state of the M ions) the materials are generally held together by closed loops of -O-M-O-M-O- linkages. The structure of the final material is governed by the reaction conditions, principally pH, temperature and the
15 ratio of the reactants. In general, it is recognised that the reactants should be added in the molar proportions that are required in the final product.

If it is desired to incorporate a heteroelement X then this is conveniently added, typically as an oxyanion, for example a silicate, as a water soluble salt. It can generally be added before or after acidification. As well as acidification it has been
20 found that the addition of the heteroelement changes the bond angles and hence the structure of the final product.

Accordingly, the present invention also provides a process for preparing a luminescent particle of the present invention which comprises dissolving a salt of an oxo/thiometallate of M in water together with a water soluble salt of M^2 , adding acid
25 to the resulting solution, subsequently adding a water soluble salt of M^1 and recovering the resulting product, a water soluble salt of an oxo/thioanion of X optionally being added prior to the addition of acid.

The particles obtained by the process typically possess a particle size not exceeding 20 nm, desirably not exceeding 10 nm, preferably not exceeding 5 nm and
30 more preferably not exceeding 2 nm. These sizes are diameters and they assume the

particles to be spherical. The particles will in fact usually be substantially spherical; and when they are not spherical the size is to be taken as the diameter of a sphere of the same volume as that of the actual particle.

The luminescent particles of the present invention find utility in a variety of ways including biotags, drug discovery/development, electroluminescent displays, both AC and DC, magnetic centres of coatings, security marking /labelling/identification, drug delivery and non destructive testing including crack detection as well as in agriculture products. For these purposes they can be delivered by, for example, inkjet, screen printing, injection, dipcoating, or spin coating.

As indicated, the particles of the present invention are particularly useful as phosphors in electroluminescent displays, both AC and DC.

The phosphors also find particular utility in security marking. For this purpose, the phosphors are dispersed in a suitable ink formulation. Typically such formulations involve a binder with the particles. Suitable binders include polymers and resins such as carboxylated acrylic resins and ethylene/vinyl ester copolymers e.g. ethylene/vinyl acetate copolymers e.g. containing about 40% vinyl acetate by weight.

Although it is believed that the particles can sometimes be used as they are for (for example) biotagging and other diagnostic purposes they are typically coated with silica or other material such as titania or zirconia to which an intermediate "biological" molecule can be attached. Alternatively the particles can be capped with an organic acid or Lewis base so that the surface of the particles possesses one or more reactive groups to which a ligand can be attached, the ligand possessing a free reactive group allowing attachment to a biological moiety. Typically ligands which can achieve this include phosphines, phosphine oxides, thiols, amines, carboxylic acids, phosphates, sulfonic acids, sulfinic acids, phosphoric acids, phosphonic acids, phosphinic acids, crown ethers and mixtures of these.

The ligand itself can be monodentate (i.e. with a single binding point, e.g. a trialkylphosphine oxide e.g. with a chain length of 4 to 20 carbon atoms), bidentate (e.g. dihydrolipoic or a dialkyl sulphosuccinate e.g. sodium dioctyl sulphosuccinate

with a similar chain length to monodentate) or multi dentate (polymer/dendrimers with pendant side groups such as phosphines, phosphine oxides, thiols, amines, carboxylic acids, phosphates, sulfonic acids, sulfinic acids, phosphoric acids, phosphinic acids and mixtures). The ligand can also be polymeric i.e. a polymer
5 possessing the desired groups. Typically, therefore, copolymers can be used derived from, for example, a vinyl carboxylic acid such as acrylic acid and a vinyl monomer possessing a group capable of binding to the particles such as vinyl phosphonic acid. For some purposes organic and/or polymeric coatings as well as polyelectrolyte coatings can be provided.

10 The following Examples further illustrate the present invention.

Example 1




15 0.025M NaWO_4 are dissolved in deionised water, the pH being >8 . The pH is adjusted to 6.5-7.5 with glacial acetic acid at $T > 80^\circ\text{C}$ (typically $85-90^\circ\text{C}$). To this is added 0.0035M DyCl_3 under vigorous stirring. A precipitation occurs, which substantially disappears with continued stirring at $T > 80^\circ\text{C}$. The remaining precipitated material is removed by filtration. The resulting material is filtered once
20 again and the solution is placed at $T > 5^\circ\text{C}$ whereupon crystallisation occurs. These crystals are washed with ethanol and recrystallised from hot water. The crystals are then dried in air at room temperature.

This preparation may also be undertaken with Sm instead of Dy to get an orange emitter.

25 Decay time of emission measured in solid form was of the order of 1.8 ms. By comparison, when the article was dissolved in water, the decay time was about 2.0 ms. This shows that decay time is similar whether the material is in solid form or in water.

30 Example 2

-8-



(NH_4)₃[Al(OH) 6Mo₆O₁₈] · xH₂O was prepared by mixing sodium molybdate (2.96 x 10⁻²M) with Al₂(SO₄)₃ (2.47 X10⁻³M) at pH 6 to 7 (altered using acetic acid), followed by refluxing for 30 minutes. Any precipitates were removed by filtration.

5 An excess of NH₄Cl was then added to the solution, forming a white precipitate, which was isolated by filtration. The solid was then dissolved in hot water and left to crystallize at 0 degrees Celsius. 0.01M (NH_4)₃[Al(OH)₆ Mo₆O₁₈] · xH₂O is dissolved in hot deionised water. To this is added an equimolar amount of TbCl₃ with continuous stirring. The reaction was stirred for 30 minutes then reduced in vacuo to

10 a powder.

Example 3



Sodium tungstate dihydrate (3g, 9.09x10⁻³M), sodium metasilicate (0.19g, 9.09x10⁻⁴M) and sodium molybdate (0.18g, 9.09x10⁻⁴) were dispersed in 5ml 3M NaCl and heated in water bath (80-90°C) until dissolved. To this was added a mixture of 1ml 37%HCl and 1ml H₂O. An initial clouding and pale green precipitate formed, but re-dissolved upon mixing in the water bath. A slight cloudiness persisted, but this was not removed by filtration. To this solution was added EuNO₃ · 5H₂O (0.19g, 4.54x10⁻⁴M) in 2ml H₂O, whilst stirring in a water bath. An immediate precipitate formed. The reaction was stopped after 1-2 minutes and allowed to cool, and the precipitate was removed by centrifugation. The clear aqueous solution luminesces under 340nm excitation and emits as two peaks in the red at 592nm and 613nm as shown in Figure 2. The solid form of the material is also strongly

25 luminescent.


The mean particle size was about 1.5 nm.

Comparison of the quantum efficiency of the solid form of (1) with a commercial Y₂O₃:Eu phosphor (known efficiency of 70%) shows that the quantum efficiency of the material is 33%. This is shown in Figure 1.

CLAIMS

1. A luminescent particle comprising one or more compounds of the formula:

5



wherein:

M^2 is a cation, M^1 is an ion of a metal capable of providing a luminescent centre or a mixture of two or more thereof, and

10

POM is a polyoxometallate, a polythiometallate or a polyoxythiometallate of at least one metal of group VA or VIA of the Periodic Table and, optionally, a hetero atom X, the amounts of X, M^1 , M^2 and POM being such as to provide overall neutrality.

2. A particle according to claim 1 wherein M^1 is Eu^{3+} , Tb^{3+} , Dy^{3+} , Tm^{3+} , Er^{3+} , Cr^{3+} , Ce^{3+} , Pr^{3+} , Sm^{3+} , Nd^{3+} , Ho^{3+} , Yb^{3+} , Ti^{4+} or Mn^{4+} .

15

3. A particle according to claim 2 wherein M^1 is Dy^{3+} , Eu^{3+} or Tb^{3+} .

4. A particle according to any one of the preceding claims wherein M is vanadium, niobium, tantalum, molybdenum or tungsten.

5. A particle according to claim 4 wherein M is molybdenum or tungsten.

20

6. A particle according to any one of the preceding claims wherein POM contains a heteroelement X.

7. A particle according to claim 6 wherein X is a transition metal or B, Al, Si, P, S, Ga, Ge, As, Se, In, Sb, Te, I, Pb or Bi.

25

8. A particle according to claim 7 wherein X is Si or Al.

9. A particle according to any one of the preceding claims in which the polyoxymetallate comprises MO_6 octahedra.

10. A particle according to any one of the preceding claims wherein M represents more than one metal.

30

11. A particle according to any one of the preceding claims wherein the

compound contains at least 15 oxygen atoms.

12. A particle according to any one of the preceding claims having a quantum efficiency that is at least 1%.

13. A particle according to claim 12 wherein the quantum efficiency is at least 5%.

14. A particle according to any one of the preceding claims wherein M^2 is an ion of hydrogen or a metal of group 1A or 2A of the Periodic Table or an optionally substituted ammonium ion, or a mixture of two or more said ions.

15. A particle according to claim 14 wherein M^2 is sodium, potassium or optionally substituted ammonium.

16. A particle according to claim 15 wherein M^2 is sodium or ammonium.

17. A particle according to any one of the preceding claims which has a diameter not exceeding 20 nm.

18. A particle according to claim 17 which has a diameter not exceeding 5 nm.

19. A particle according to any one of the preceding claims which possesses a coating rendering the particle suitable for biotagging application.

20. A particle according to claim 19 wherein the coating is of silica.

21. A particle according to claim 1 substantially hereinbefore described.

22. A process for preparing a particle as claimed in any one of the preceding claims which comprises dissolving a water soluble salt of an oxo/thiometallate of M and optionally of an oxo/thioanion of X and a water soluble salt of M^2 in water, adding acid, and then adding a water soluble salt of M^1 and recovering the resulting product.

23. A process according to claim 22 wherein the salts are all of M^2 .

24. A process according to claim 22 or 23 wherein the acid is acetic acid or hydrochloric acid.

25. A process according to any one of claims 22 to 24 wherein the mixture is heated before the acid is added.

26. A process according to any one of claims 22 to 25 wherein a water

-11-

soluble salt of an oxo/thio anion of X is added with the water soluble salt of the oxo/thiometallate of M.

27. A process according to claim 22 substantially as described in any one of the Examples.

5 28. A particle as claimed in any of claims 1 to 21 for use in biotagging, drug discovery/development, electroluminescent displays, magnetic centres of coatings, security marking/labelling/identification, drug delivery, non-destructive testing or in agricultural products.

1/2

5





FIGURE 1

25

30

2/2

5



10

FIGURE 2

INTERNATIONAL SEARCH REPORT

International Application No
PCT/GB 03/03649

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C09K11/78 C09K11/67 C09K11/68 C09K11/69 C09K11/82

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 C09K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, INSPEC, PAJ, IBM-TDB, CHEM ABS Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 3 881 941 A (KERNOHAN JOHN A) 6 May 1975 (1975-05-06) the whole document	1-5, 11-16, 21-25,27
X	EP 0 363 977 A (EASTMAN KODAK CO) 18 April 1990 (1990-04-18) the whole document ----- -/--	1,4

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the International filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- "a" document member of the same patent family

Date of the actual completion of the international search

6 February 2004

Date of mailing of the international search report

11 02 2004

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Drouot, M-C

INTERNATIONAL SEARCH REPORT

International Application No
PCT/GB 03/03649

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P,X	<p>WANG J ET AL: "Luminescence properties of LB films based on heteropolytungstate of rare earth"</p> <p>MATERIALS SCIENCE AND ENGINEERING B, ELSEVIER SEQUOIA, LAUSANNE, CH, vol. 97, no. 1, 15 January 2003 (2003-01-15), pages 83-86, XP004399819</p> <p>ISSN: 0921-5107</p> <p>pages 83-86</p>	1-5, 11-16
P,X	<p>-----</p> <p>WANG J ET AL: "Langmuir-Blodgett films based on europium-substituted heteropolytungstate and their luminescence properties"</p> <p>JOURNAL OF LUMINESCENCE, AMSTERDAM, NL, vol. 101, no. 1-2, January 2003 (2003-01), pages 63-70, XP004398333</p> <p>ISSN: 0022-2313</p> <p>pages 63-70</p>	1-8, 11-15
P,X	<p>-----</p> <p>WANG J ET AL: "Luminescent self-assembled thin films based on rare earth-heteropolytungstate"</p> <p>MATERIALS LETTERS, NORTH HOLLAND PUBLISHING COMPANY, AMSTERDAM, NL, vol. 57, no. 5-6, January 2003 (2003-01), pages 1210-1214, XP004399990</p> <p>ISSN: 0167-577X</p> <p>page 1210 - page 1214</p>	1-5, 11-16
A	<p>-----</p> <p>WANG J ET AL: "Study on highly ordered luminescent Langmuir-Blodgett films of heteropolytungstate complexes containing lanthanide"</p> <p>PREPARATION AND CHARACTERIZATION, ELSEVIER SEQUOIA, NL, vol. 415, no. 1-2, 1 August 2002 (2002-08-01), pages 242-247, XP004380245</p> <p>ISSN: 0040-6090</p> <p>pages 242-247</p>	1-5, 11-16
X	<p>-----</p> <p>WANG J ET AL: "Effective energy transfer and luminescence of LB films based on europium-substituted heteropolytungstate"</p> <p>PREPARATION AND CHARACTERIZATION, ELSEVIER SEQUOIA, NL, vol. 414, no. 2, 22 July 2002 (2002-07-22), pages 256-261, XP004375010</p> <p>ISSN: 0040-6090</p> <p>pages 256-261</p> <p>-----</p> <p>-/--</p>	1-8, 11-15

INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 03/03649

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	KUBOTA S-I ET AL: "Luminescence properties of Gd _{1-x} BixTa ₇ O ₁₉ (0<x<1)" JOURNAL OF ALLOYS AND COMPOUNDS, ELSEVIER SEQUOIA, LAUSANNE, CH, vol. 281, no. 2, 18 December 1998 (1998-12-18), pages 181-185, XP004182319 ISSN: 0925-8388 pages 181-185	1,4,6,7, 11-13
X	----- KUBOTA S-I ET AL: "Luminescence properties of rare earth ions in polytantalate" JOURNAL OF ALLOYS AND COMPOUNDS, ELSEVIER SEQUOIA, LAUSANNE, CH, vol. 275-277, 24 July 1998 (1998-07-24), pages 746-749, XP004183994 ISSN: 0925-8388 pages 746-749	1-4
A	----- DATABASE WPI Section Ch, Week 199812 Derwent Publications Ltd., London, GB; Class L03, AN 1998-129160 XP002260487 & SU 1 506 819 A (AS USSR URALS CHEM INST) 20 April 1997 (1997-04-20) abstract	1-4
X	----- DATABASE INSPEC [Online] THE INSTITUTION OF ELECTRICAL ENGINEERS, STEVENAGE, GB; 1972, FORMAN R A ET AL: "Optical spectroscopy of some chromium heteropolymolybdate salts" XP002260484 Database accession no. 570294 abstract & 11TH EUROPEAN CONGRESS ON MOLECULAR SPECTROSCOPY (ABSTRACTS ONLY RECEIVED), TALLINN, USSR, 28 MAY-1 JUNE 1973, 1972, page 1 pp., 1972, Tallinn, USSR, Acad. Sci., Estonian SSR, USSR	1,2,4,5, 11,14-16
P,X	----- WANG J ET AL: "Luminescence properties of rare earth-polyoxometalate thin film deposited by sol-gel process" MATERIALS LETTERS, NORTH HOLLAND PUBLISHING COMPANY, AMSTERDAM, NL, vol. 56, no. 3, October 2002 (2002-10), pages 300-304, XP004387846 ISSN: 0167-577X pages 300-304	1-5, 11-16
	----- -/--	

INTERNATIONAL SEARCH REPORT

International Application No

PC/GB 03/03649

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	XU L ET AL: "Preparation, characterization and luminescence properties of ultrathin films containing polyoxometalates" MATERIALS LETTERS, NORTH HOLLAND PUBLISHING COMPANY, AMSTERDAM, NL, vol. 54, no. 5-6, June 2002 (2002-06), pages 452-457, XP004354290 ISSN: 0167-577X pages 452-457	1-8, 11-15
X	----- LIS S ET AL: "Spectroscopic studies of Eu(III) and Nd(III) complexes with several polyoxometalates" JOURNAL OF ALLOYS AND COMPOUNDS, ELSEVIER SEQUOIA, LAUSANNE, CH, vol. 300-301, April 2000 (2000-04), pages 370-376, XP004192564 ISSN: 0925-8388 pages 370-376	1-16
X	----- LIS S: "Applications of spectroscopic methods in studies of polyoxometalates and their complexes with lanthanide(III) ions" JOURNAL OF ALLOYS AND COMPOUNDS, ELSEVIER SEQUOIA, LAUSANNE, CH, vol. 300-301, April 2000 (2000-04), pages 88-94, XP004192521 ISSN: 0925-8388 pages 88-94	1-9, 11-16
X	----- ANTONIO M R ET AL: "Coordination and valence of europium in [Eu(alpha-2-As2W17O61)2]<17-> and [Eu(W5O18)2]<9->" JOURNAL OF ALLOYS AND COMPOUNDS, ELSEVIER SEQUOIA, LAUSANNE, CH, vol. 275-277, 24 July 1998 (1998-07-24), pages 827-830, XP004184013 ISSN: 0925-8388 pages 827-830	1-8, 11-16
X	----- YAMASE T ET AL: "ELECTROLUMINESCENCE CELL BASED ON POLYOXOMETALATES PULSED ELECTRIC FIELD-INDUCED LUMINESCENCE OF DECATUNGSTOEUROPATE LAYERS" JOURNAL OF THE ELECTROCHEMICAL SOCIETY, ELECTROCHEMICAL SOCIETY, MANCHESTER, NEW HAMPSHIRE, US, vol. 140, no. 8, 1 August 1993 (1993-08-01), pages 2378-2384, XP000403634 ISSN: 0013-4651 page 2378 - page 2384 ----- -/--	1-8, 11-16,28

INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 03/03649

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	<p>DATABASE INSPEC [Online] THE INSTITUTION OF ELECTRICAL ENGINEERS, STEVENAGE, GB; 1998, LIS S ET AL: "Spectroscopic characterisation of luminescent Eu(III)/polyoxometalate sandwiched and encrypted complexes" XP002260485 Database accession no. 6435118 abstract & RARE EARTHS '98. INTERNATIONAL CONFERENCE, FREMANTLE, WA, USA, 25-30 OCT. 1998, vol. 315-317, 1998, pages 431-438, Mater. Sci. Forum (Switzerland), Materials Science Forum, 1999, Trans Tech Publications, Switzerland ISSN: 0255-5476</p>	1-16
P,X	<p>----- DATABASE INSPEC [Online] THE INSTITUTION OF ELECTRICAL ENGINEERS, STEVENAGE, GB; 15 January 2003 (2003-01-15), LIN XU ET AL: "Preparation and characterization of photoluminescent ultrathin films based on polyoxometalates" XP002260486 Database accession no. 7485574 abstract -----</p>	1-16

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 03/03649

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 3881941	A	06-05-1975	DE 2446433 A1	10-04-1975
			GB 1490722 A	02-11-1977
			JP 870996 C	20-07-1977
			JP 50061385 A	26-05-1975
			JP 51048470 B	21-12-1976

EP 0363977	A	18-04-1990	DE 68913253 D1	31-03-1994
			DE 68913253 T2	08-09-1994
			EP 0363977 A1	18-04-1990
			JP 2149840 A	08-06-1990
			US 5132192 A	21-07-1992

SU 1506819	A	20-04-1997	SU 1506819 A1	20-04-1997

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

☐ BLACK BORDERS

☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES

☐ FADED TEXT OR DRAWING

☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING

☐ SKEWED/SLANTED IMAGES

☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS

☐ GRAY SCALE DOCUMENTS

☒ LINES OR MARKS ON ORIGINAL DOCUMENT

☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY

☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.